

# LAMIWOOD UNDERLAY

## Cellular Sponge Rubber Underlay

Ideal for use under Laminate and Solid Timber Floors

Suitable for General Contract and Domestic Use

Made from Quality Natural Rubber

Increased Sound Insulation

Moisture resistant properties

Roll Size : 1.37 m x 11.0 m

### Test results BS 5808:1991

Specification	BS Requirements	Result	Method
Weight		2123 g/m <sup>2</sup>	
Thickness Variance from standard thickness		2.5 mm +/- 0.5 mm	BS4051
Breaking Strength	Minimum 40 N		BS 2576
Length		130N	
Width		80N	
Extension under force			
Length	Max 10% @40N	1.2%	
Width		2.1%	
Loss in thickness after dynamic loading	Max 15% after 1000 impacts	8.9 %	BS 4052
Loss in thickness after static loading	Max 15% after 24 hrs	13.5%	BS4939
Resistance to cracking	No greater than 50 mm	Pass	BS 5808
Odour		No objectionable odour	
Acoustic	Weighted impact sound Improvement index (Delta Lw)	20dB	ISO 140-8:1998
Resistance to moisture		Impermeable : 0.001 foil and thicker is impermeable to moisture	